

# PermaTone

# Modena™

## Modena

An acrylic, rustic, Venetian plaster finish is formulated with integral coloring, silica fillers, and chemical additives. Modena is water based, environmentally safe, vapor permeable, mildew resistant, scratch and abrasion resistant and cleanable.

### RECOMMENDED USE

Interior commercial, hospitality, military, educational and residential wall applications. Modena may be applied over properly prepared drywall, CMU block, masonry, plaster or concrete.

### COVERAGE

Each 5 gallon pail provides approximately 250 to 300 ft<sup>2</sup> of coverage with 2 coats. Variations in substrate conditions, applicator technique and skill level will affect coverage.

### PACKAGING

1 gallon pail: 12 lbs. net, 12.7 lbs. gross  
5 gallon pail: 60 lbs. net, 62.8 lbs. gross

### COLORS

Modena can be tinted to match almost any color.

### PROPERTIES

#### Drying Time

**Initial Set:** 1-2 hrs. @ 70°F, 50% RH

**Cure:** 72 hrs. @ 70°F, 50% RH

#### VOC Compliance:

Modena complies with all known regulations limiting the Volatile Organic Compound (VOC) content of architectural coatings and sealers.

### EQUIPMENT

Stainless steel trowel with rounded corners and beveled edges; flexible metallic spatula; knock down and sand paper #250 or #320.

### APPLICATION

#### Surface Preparation

Surfaces must be smooth, clean, dry, paint ready, and free of dust, grease or other materials that may affect bonding. Previously painted surfaces must be scraped to remove all loose paint. Vinyl wall coverings and wallpaper must be removed along with any excess adhesive.

Use CorevMix surface leveler to repair surface imperfections and to skim over adhesive residue.

Prime with PintuFondo tinted to the desired base color. See surface preparation instructions for Modena and PintuFondo in the PermaTone Application Guide for further information.

#### Application Procedure

Apply the first layer using short strokes and irregular patterns. Allow the first coat to dry 8 hours. Apply a second coat in the same manner and allow to set for 20 -25 minutes, depending on room temperature and humidity. To achieve the desired gloss and mottled appearance, repeatedly press down and slide the trowel edge over the surface of the final coat, holding a 5-10° angle to the surface. See the PermaTone Application Guide for additional information about Modena.

#### CLEAN-UP

Tools and overspray should be cleaned with water while Modena is still wet.

#### STORAGE

Store Modena in its original containers at temperatures not less than 40°F (4°C) or greater than 90°F (32°C). Store out of direct sunlight. Do not stack pails more than three high.

#### SHELF LIFE

Approximately one year if stored properly.

#### MAINTENANCE

To clean, use a medium bristle brush or damp cloth and a mild soap and water solution.

#### WARRANTY

Modena is conditionally warranted for 10 years against delamination and color fading. This warranty does not apply to any party constituting a "consumer" for purposes of the Magnuson-Moss Warranty Act. All other warranties, whether expressed or implied, including without limitation any warranty of merchantability or fitness for purpose, are expressly disclaimed.

#### LIMITATIONS

For use on interior wall surfaces only. Patching limitations standard to applied coatings.

- This product requires skilled application.
- Surface air and substrate temperatures shall be 60°F to 85°F during application and for a period of 24 hours thereafter.
- Modena is not compatible with solvent base products or cleaners.
- Use in well ventilated areas.
- Protect all adjacent surfaces (door frames, windows, etc.) adequately.
- Do not water down material.
- Do not apply over quickset joint compound.
- Prepare metal surfaces such as corner bead with rust inhibitors prior to application of Modena.
- Always wear appropriate eye and skin protection when using this product.
- Harmful if swallowed.
- Avoid constant moisture in the wall cavity behind the coating.

Information contained in this bulletin conforms to the standard detail recommendations and specifications for the installation of PermaTone products, is presented in good faith, and is applicable as of the date of this document. PermaTone assumes no liability, expressed or implied as to the architecture, engineering, or workmanship of any project.

**PermaTone**

#### PermaTone, Inc.

11620 Brittmoore Park Drive  
Houston, Texas 77041  
713/937-3437 TEL  
713/849-9114 FAX  
877/737-6286 TOLL FREE  
www.permatone.com

Made in the U.S.

