

Palladio™

Palladio

A permeable Venetian Stucco with a polished marble appearance. PALLADIO is a decorative finish formulated with acrylic resins, organic and inorganic pigments, mineral fillers, and chemical additives that enhance the coatings performance.

RECOMMENDED USE

PALLADIO is ideal for elegant interior spaces requiring dramatic accents and unique appearance.

COVERAGE

Each gallon provides approximately 120-180 ft² of coverage, with approximately 6-8 dry mils in two coats over a smooth and uniform COREVMIX surface.

PACKAGING

1/2 gal. pail: 5.6 lbs. net, 5.8 lbs. gross
1 gal. pail: 11.2 lbs. net, 11.7 lbs. gross
5 gal. pail: 56 lbs. net, 58.8 lbs. gross

PROPERTIES

Drying Time

Initial Set: 1-2 hrs. @ 77°F, 50% RH
Cure: 72 hrs. @ 77°F, 50% RH

THINNING

Not required or recommended.

EQUIPMENT

Stainless steel trowel with rounded corners and beveled edges, Flexible stainless steel spatula, Sandpaper #150 and #320

VOC Compliance:

PALLADIO complies with all known regulations limiting the Volatile Organic Compound (VOC) content of architectural coatings and sealers.

SURFACE PREPARATION

Walls must be paint ready. Surfaces must be clean, dry and free of dust, grease or other materials that may affect bonding. Previously painted surfaces must be scraped to remove all loose paint. Interior drywall joints must be taped, floated and sanded using normal interior drywall finishing procedures. Use COREVMIX to repair minor drywall damage.

MATERIAL PREPARATION

Manually mix PALLADIO until homogeneous. Do not use a high-speed mixer.

APPLICATION

Using a stainless steel trowel, skim the entire surface with COREVMIX surface leveler. Allow the COREVMIX to dry for 12 hours and sand the surface smooth using a #150 and #400 sandpaper. Remove all dust with a moist cloth. *Surface imperfections may show through the final finish.*

Using the recommended spatula or trowel, apply the first layer of PALLADIO with short strokes and irregular pattern. Avoid ANY material buildup. Each coat thickness should not exceed 9 mils. Allow the first coat to dry 8 hours. Sand down any imperfections with #320 or #400 sandpaper.

Using a moist cloth remove all dust. Allow the surface to dry thoroughly before beginning application of subsequent coats of PALLADIO. At least two coats will be necessary.

To achieve the desired gloss, polish the PALLADIO surface on the final coat by repeatedly pressing down and sliding the trowel's edge over the surface holding a 5° to 10° angle with the surface.

STORAGE

Store PALLADIO in its original container at temperatures not less than 40°F (4°C) nor greater than 90°F (32°C). Store in covered space, out of direct sunlight.

Do not stack pails more than three high.

SHELF LIFE

Approximately six months if stored properly.

MAINTENANCE

Surface may be cleaned of minor stains with a damp cotton cloth using light pressure.

WARRANTY

PALLADIO is conditionally warranted for 5 years against delamination, color fading and mildew growth. FOR COMPLETE INFORMATION, CONSULT PERMATONE'S LONG FORM SPECIFICATIONS AND PRODUCT WARRANTIES. This warranty does not apply to any party constituting a "consumer" for purposes of the Magnuson-Moss Warranty Act. All other warranties, whether expressed or implied, including without limitation any warranty of merchantability or fitness for purpose are expressly disclaimed.

LIMITATIONS

- This product requires skilled application.
- Surface air and substrate temperature must be 40°F or higher during application and for 24 hours thereafter.
- PALLADIO is not compatible with solvent-based coatings and cleaners.
- Use in a well ventilated area.
- Wear face and eye protection during application.
- Not recommended for walls where high commercial traffic and surface abrasion is expected.
- This product requires skilled application.
- Use eye and face protection.
- Avoid constant moisture in the wall cavity behind the coating.

The logo for PermaTone, featuring the word "Perma" in a bold, blue, sans-serif font and "Tone" in a red, cursive script font.

PermaTone, Inc.

11620 Brittmoore Park
Drive Houston, Texas
77041 713/937-3437 TEL
713/849-9114 FAX
877/737-6286 TOLL FREE
www.permatone.com

Made in the U.S.

PermaTone®

05-19