

PermaTone™

Tevere

A Permeable Venetian stucco with a refined old-world matte finish, TEVERE is a decorative finish reminiscent of the finest Renaissance craftsmen. It is formulated with acrylic resins, organic and inorganic pigments, mineral fillers and chemical additives that enhance the coatings performance.

RECOMMENDED USE

TEVERE is an ideal choice for elegant interior wall spaces where visually dramatic and old-world accents are desired. Without the high-gloss polished plaster look, layers of color create depth and texture that greatly enhance either classical or contemporary settings.

COVERAGE

Each gallon provides approximately 65-85 ft² of coverage with a two-coat application over a smooth COREVMIX surface.

PROPERTIES

Drying Time

Initial Set: 2 hrs. @ 77°F, 50% RH

Cure: 72 hrs. @ 77°F, 50% RH

PACKAGING

1 gal. pail: 10.2 lbs. net, 10.9 lbs. gross

5 gal. pail: 56 lbs. net, 58.8 lbs. gross

REDUCTION

Not required or recommended.

EQUIPMENT

- Stainless steel trowel with rounded corners and beveled edges
- Flexible metallic spatula
- Sandpaper #150, #320

VOC Compliance

QuartzSilco complies with all known regulations limiting the Volatile Organic Compound (VOC) content of architectural coatings and sealers.

APPLICATION

Surface Preparation

Walls must be prepared to be paint ready. Surfaces must be clean, dry and free of dust, grease or other materials that may affect bonding. Previously painted surfaces must be scraped to remove all loose paint. Interior drywall must be taped, floated and sanded using normal interior drywall finishing procedures. Use COREVMIX surface leveler to repair minor drywall damage.

Material Preparation

Manually mix TEVERE until homogeneous.

Application Procedures

Using a stainless steel trowel, skim the entire wall with COREVMIX. Allow the COREVMIX to dry for 12 hours and sand the surface smooth using a #150-#320 sandpaper. *Surface imperfections might show through the final finish.*

Remove all dust with a moist cloth.

Using a stainless steel trowel, apply the first layer of TEVERE using short strokes with irregular pattern avoiding ANY material buildup. Each coat thickness should not exceed 9-11 mils. Allow the first coat to dry 8 hrs. Sand down any imperfections with #320 sandpaper. Using a moist cloth remove all dust. Apply a second coat in the same manner as the first.

To achieve the desired satin and mottled appearance, polish the TEVERE surface on the final coat by repeatedly pressing down and sliding the trowels edge over the surface holding a 5° to 10° angle with the surface. Do not over polish. Contrast within the finish will increase as the product dries.

STORAGE

Store TEVERE in its original container at temperatures not less than 40°F (4°C) or greater than 90°F (32°C). Store in covered space, out of direct sunlight.

Do not stack pails more than three high.

SHELF LIFE

Approximately six months if stored properly.

MAINTENANCE

Surface may be cleaned of minor stains with a damp cotton cloth.

WARRANTY

TEVERE is conditionally warranted for 5 years against delamination and color fading. FOR COMPLETE INFORMATION CONSULT PERMATONE'S LONG FORM SPECIFICATIONS AND PRODUCT WARRANTIES. This warranty does not apply to any party constituting a "consumer" for purposes of the Magnuson-Moss Warranty Act. All other warranties, whether expressed or implied, including without limitation any warranty of merchantability or fitness for purpose are expressly disclaimed.

LIMITATIONS

- This product requires skilled application.
- Surface air and substrate temperature must be 40°F or higher during application and for 24 hrs. thereafter.
- TEVERE is not compatible with solvent based coatings and cleaners.
- The use of COREVMIX as a base optimizes the coverage of TEVERE, making an easier and more durable application.
- Wear face and eye protection during application.
- Use in a well ventilated area.
- Not recommended for walls where high commercial traffic and surface abrasion is expected.

The logo for PermaTone features the word "PermaTone" in a bold, blue, sans-serif font. The letter "T" is stylized with a multi-colored gradient (red, orange, yellow, green, blue) that flows through it.

PermaTone, Inc.

11620 Brittmoore Park Drive

Houston, Texas 77041

832/243-0787 TEL

713/937-9765 FAX

www.permatone.com

PermaTone and the PermaTone logo are registered trademarks of PermaTone, Inc.