



11620 Brittmoore Park Drive
Houston, TX 77041

Specs: Light Damascus

- **QuartzSilco®** is an Acrylic polymer based interior textured coating which can be applied to create a variety of Textured looks.
- **PintuFondo®** is a high solids , high permeable undercoat for the QuartzSilco Textured finish

The following Tables summarizes the data for ASTM D2486-6 for the two component products of the Light Damascus Texture .

Samples were applied to a total of 27 mil WFT on Leneta and allowed to cure for 14 days. After 14 days, 4 samples were tested using the ASTM D2486-6 scrub resistance test. The following results were obtained.

The sample was weighed initially and weighed again after 3000 cycles on the scrub machine QPI 2500. No cracking or complete failure was noted.

	Sample #1	Sample #2	Sample #3	Sample #4
Initial Weight	6.7491	5.4270	5.8152	5.5480
Weight at 48 hours	6.2357	4.9490	5.3988	4.9401
Weight at 72 hours	6.2341	4.9482	5.3972	4.9387
Average Final Weight Percent	6.2349	4.9486	5.3980	4.9394
Lost	7.6188	8.8152	7.1743	10.9697

Average Percent Lost **8.6445%**

of scrub cycles before failure

Sample #1	4476
Sample #2	4525
Sample #3	4532
Sample #4	4476
Average of all samples	4521.5

Internal Data

PintuFondo:
Density: 11 lbs/gl
Vis: 45,000 cps
pH: 9.0
Temp: 26.4°C

QuartzSilco:
Density: 12 lbs/gl
Vis: 130,000 cps
pH: 8.3
Temp: 23.8°C

PERMANTONE, INC